

# **DESIGN OF HIGH EARLY PERFORMANCE CONCRETE WITH THE ADDITIONAL MATERIAL OF FLY ASH AND SILICA FUME**

## **Final Project**

To fulfill part of the requirements  
To reach a Bachelor Degree of Civil Engineering



Submitted by:  
**BUDI PRAKOSO**  
**D 100 122 001**

**CIVIL ENGINEERING PROGRAM**  
**ENGINEERING FACULTY**  
**MUHAMMADIYAH SURAKARTA UNIVERSITY**  
**2018**

## **APPROVAL SHEET**

### **DESIGN OF HIGH EARLY PERFORMANCE CONCRETE WITH THE ADDITIONAL MATERIAL OF FLY ASH AND SILICA FUME**

#### **Final Project**

Submitted and defended in Final Examination of  
Final Project in Front of Board of Examiner On 16 July 2018

Submitted by:


**BUDI PRAKOSO**  
**NIM : D100122001**

Supervisor




**Muhammad Ujjanto, S.T., M.T.**  
NIK. 728

Examiner I



**Ir. Subendro Trinugroho, M.T.**  
NIK. 732

Examiner II



**Yenny Nurchasanah, S.T., M.T.**  
NIK. 921

## VALIDITY SHEET

### DESIGN HIGH EARLY PERFORMANCE CONCRETE WITH THE ADDITIONAL MATERIAL FLY ASH AND SILICA FUME

#### Final Project

Submitted and defended in Final Examination of  
Final Project in Front of Board of Examiner On 16 July 2018

Submitted by:

**BUDI PRAKOSO**  
**NIM : D100122001**


Supervisor

  
**Muhammad Ujjanto, S.T., M.T.**  
NIK. 728

Examiner I

  
**Ir. Suhendro Trinugroho, M.T.**  
NIK. 732

Examiner II



  
**Yenny Nurchasanah, S.T., M.T.**  
NIK. 921

This Final Project is Accepted in partial to fulfill of the requirements



To reach a Bachelor Degree of Civil Engineering

Surakarta, July 2018

Dean of Engineering Faculty

  
  
**Ir. Sri Sunarjono, M.T., Ph.D.**  
NIK. 682

Head of Civil Engineering Program Study

  
  
**Dr. Mochamad Soikin, M.T., Ph.D.**  
NIK. 792

# ORIGINALITY STATEMENT OF PUBLICATION MANUSCRIPT

The undersigned, I am:

Name : BUDI PRAKOSO

NIM : D 100 122 001

Faculty/Department : ENGINEERING/ CIVIL ENGINEERING

Title : DESIGN OF HIGH EARLY PERFORMANCE  
CONCRETE WITH THE ADDITIONAL OF  
MATERIAL FLY ASH AND SILICA FUME

:

1. Grant may royalty - free right to UMS Library of author of my scientific work, for the shake of scientific science development.
2. Grant the right to save, transfer provide / transfer information, manage in database from me as long as I keep my name as the author / creator.
3. Willing and guaranteed personally without involving the UMS library, of all form of lawsuits that are appear for copyright infringement in this scientific work.

Surakarta, 16 July 2018

Author



**BUDI PRAKOSO**

NIM. D100122001

## **PREFACE**

*AssaalamualaikumWr. Wb*

Thank to Almighty God who has given His bless to the writer for finishing the final report in the form of laboratory experiment, entitled "Design of High Performance Concrete Early with The Additional Material and Fly Ash Silica Fume". This Final Project is prepared to meet some of the requirements of completing an undergraduate program at the Faculty of Engineering Department of Civil Engineering University of Muhammadiyah Surakarta.

The author also want to express his deep and sincere gratitude for those who have guided in completing this Final Project. The greatest honor and appreciation would be finally dedicated to:

- 1) Mr Ir. Sri Sunarjono, MT, PhD.,as the Dean of Engineering Faculty of Universitas Muhammadiyah Surakarta.
- 2) Mr Mochamad Solikin, ST. MT. PhD., as the Head of Civil Engineering of Universitas Surakarta.
- 3) Mr Anto Budi Listyawan, S.T., M.Sc., as academic advisor.
- 4) Mr. Muhammad Ujianto, S.T., M.T., as advisor for the final project who has given many suggestion for guide and taughtt author.
- 5) Mr. Ir Suhendro Trinugroho,M.T., as first examiner who give some advice and guidance for the author.
- 6) Mrs. Yenny Nurchasanah, S.T., M.T.. as first examiner who give some advice to make this final project better.
- 7) All lecturers in Civil Engineering Departement of Engineering Faculty of Universitas Muhammadiyah Surakarta for all the knowledge, patience and the guidance that has been given to the author.
- 8) Lecturer at the Faculty of Civil Faculty of Universitas Muhammadiyah Surakarta gratitude for the guidance and knowledge that has been given.

- 9) Mr Ir. A. Karim Fatchan, M.T as Head of Laboratory of Civil Engineering Study Program of Muhammadiyah University of Surakarta
- 10) Mr. Rohani, Spd. as Secretary of Administration Department of Civil Engineering University of Muhammadiyah Surakarta.
- 11) Friends of Civil Engineering 2012 students who have assisted the research
- 12) Other parties that can not mention one by one author.

The author realizes that this Final Report is still far from perfect, so with all the humility, criticism and constructive suggestions, the writer hopes to improve the report in the future, and hopefully this Final Report can be useful for all of us. Amin.

Wassalamu'alaikumWr Wb.

Surakarta, May 2016

Author

## **DESIGN OF HIGH EARLY PERFORMANCE CONCRETE WITH THE ADDITIONAL MATERIAL OF FLY ASH AND SILICA FUME**

### **Abstrak**

Dari hasil penelitian, ditemukan bahwa kekuatan beton tertinggi ditemukan pada 0% campuran abu terbang yaitu 8,12 MPa pada umur 6 jam dan 18,31 MPa pada umur 24 jam. Kekuatan beton terendah ditemukan pada fly ash 10% fly ash Campuran penggantian yaitu 6,61 MPa pada usia 6 jam dan 14,91 pada usia 24 jam. Selanjutnya, ditemukan bahwa kekuatan beton tertinggi ditemukan pada 0% campuran pengganti fly ash yaitu 24,53 MPa pada umur 3 hari dan kekuatan beton terendah ditemukan pada fly ash 10% fly ash Campuran penggantian yaitu 19,44 MPa pada usia 3 hari. Dalam penelitian ini menentukan rencana  $f_c$  '60 MPa tetapi dari hasil penelitian, ditemukan  $f_c$  terjadi sama dengan 61,34 MPa, sehingga kekuatan kompresif rencana dapat tercapai.

Kata kunci: kuat tekan, fly ash, silica fume, superplasticize

### **Abstract**

From the research, it was found that the highest strength of concrete was found in 0% fly ash replacement mixture that is 8.12 MPa at the age of 6 hours and 18.31 MPa at age of 24 hours. The lowest strength of concrete was found in fly ash 10% fly ash Replacement mixture that is 6.61 MPa at the age of 6 hours and 14.91 at age of 24 hours. Furthermore, it was found that the highest strength of concrete was found in 0% fly ash replacement mixture that is 24.53 MPa at the age of 3 days and the lowest strength of concrete was found in fly ash 10% fly ash Replacement mixture that is 19.44 MPa at the age of 3 days. In this study determine  $f_c$  plan of 60 MPa but from result of research, found  $f_c$  happened equal to 61.34 MPa, so compressive strength of plan can be reached.

**Keywords:** *compressive strength, fly ash, silica fume, superplasticizer*

## LIST OF CONTENT

<b>TITLE PAGE .....</b>	<b>i</b>
<b>APPROVAL SHEET.....</b>	<b>ii</b>
<b>VALIDITY SHEET .....</b>	<b>iii</b>
<b>ORIGINALITY STATEMENT OF PUBLICATION MANUSCRIPT ...</b>	<b>iv</b>
<b>PREFACE .....</b>	<b>v</b>
<b>ABSTRACT .....</b>	<b>vii</b>
<b>LIST OF CONTENTS .....</b>	<b>viii</b>
<b>LIST OF FIGURES .....</b>	<b>xi</b>
<b>LIST OF TABLE .....</b>	<b>xii</b>
<b>LIST OF NOTATION .....</b>	<b>xiii</b>

### CHAPTER I. INTRODUCTION

1.1 Background.....	1
1.2 Formulation of The Problem .....	2
1.3 Research Objectives .....	2
1.4 Research Benefits.....	2
1.5 Scope .....	2

### CHAPTER II. LITERATURE RIVIEW

2.1 General Definition .....	4
2.1. The results of the study as a review	
1. Fandhi Hernando, 2009 .....	5
2. Yusuf Setya Prabowo, 2014.....	5
3. Muhammad Rifai Syakuri and Haryadi, 1997 .....	5
4. Li and Antasari, 2000 .....	5

### CHAPTER III. BASIC THEORY



3.1 Concrete .....	7
3.2 Portland Cement .....	7
3.3 Water .....	8
3.4 Aggregate .....	9
3.5 Additional Material .....	
3.5.1 Fly Ash .....	14
3.5.2 Silica Fume .....	15
3.5.1 Superplasticizer .....	15
3.6 Workability .....	16
3.7 Water Cement Ratio .....	17
3.8 Slump .....	17
3.9 Concrete Compressive Strength .....	17
3.10 Concrete Mix design .....	18

#### **CHAPTER IV. RESEARCH METHODOLOGY**

4.1 Material .....	28
4.2 Equipment.....	28
4.3 Speciment .....	29
4.4 Research Phase .....	29
4.5 Research Step .....	32

#### **CHAPTER V. RESEARCH RESULT AND DISCUSSION**

5.1 General .....	33
5.2 Material Testing result .....	
5.2.1 The Result of Fine Aggregate Testing .....	33
5.2.2 The Result of Course Aggregate Testing .....	36
5.3 Mix Concrete design.....	40
5.4 Test Result.....	
5.4.1 Slump Test Result .....	43
5.4.2 Test result of Concrete Specific Gravity .....	44
5.2.3 The Result of Compressive Strength.....	44

## **CHAPTER VI. CONCLITIONS AND SUGGESTIONS**

6.1 Conclutions .....	50
6.2 Suggestations .....	50

## LIST OF FIGURE

Figure IV. 1. Flowchart of Research Step.....	32
Figure V. 1. Fine Aggregate Graduation Graph.....	35
Figure V. 2. Course Aggregate Graduation Graph .....	39
Figure V. 3. Concrete Compressive Strength Test Result .....	48

## LIST OF TABLE

Table III. 1. Fine aggregate gradation .....	11
Table III. 2. Course aggregate gradation.....	14
Table III. 3. Chemical Composition Fly Ash Paiton (% mass).....	15
Table III. 4. Volume Fraction Coarse Aggregates Suggested.....	22
Table III.5. Estimated First Water needs Mixing and Air Content of Fresh Concrete with 35% Based Sand Air Cavity .....	23
Table III. 6. Recommended Maximum Ratio W/ (c + p) (No Superplasticizer) .....	23
Table III. 7. Recommended Maximum Ratio (with Superplasticizer).....	24
Table IV. 1. Specimen.....	29
Table V. 1. The results of fine aggregate testing .....	33
Table V .2. The results of fine aggregate gradation testing .....	34
Table V. 3. The results of course aggregate testing .....	36
Table V. 4. The results of course aggregate gradation testing .....	37
Table V. 5. Fine modulus calculation .....	38
Table V. 6. Proportion of mixture of concrete mixture for 1 m <sup>3</sup> .....	41
Table V. 7. Proportion of mixture of concrete mixture for 1 concrete cylinder mold .....	41
Table V. 8. Proportion of mixture of concrete mixture for each variation every time mixing .....	42
Table V. 9. Slump value of each variation.....	43
Table VI. 10. Specific gravity of each variation .....	44
Table VI. 11. Concrete compressive strength test results at 6 hours .....	45
Table VI. 12. Concrete compressive strength test results at 24 hours .....	45
Table VI. 13. Concrete compressive strength test results at 3 days.....	46
Table VI. 14. Concrete compressive strength test results at 28 days.....	46

## LIST OF NOTATION

SNI	: Standar Nasional Indonesia
PC	: Portland Cement
$f_c'$	: the specified compressive strength of concrete (MPa)
MPa	: Mega Pascal
A	: Surface area of the test object ( $\text{cm}^2$ )
$P_{\max}$	: Load maximal (kN)
t	: High of concrete
W	: Weight of concrete (kg)
BP 1	: Concrete with superplasticizer
BP 2	: Concrete with 0 % fly ash, 5 % silica fume, superplasticizer
BP 3	: Concrete with 5 % fly ash, 5 % silica fume, superplasticizer
BP 4	: Concrete with 10 % fly ash, 5 % silica fume, superplasticizer